



FINSA

Financiera Maderera, S.A. -FINSA-
Carretera N-550, km. 5
15890 SANTIAGO DE COMPOSTELA
SPAIN

DECLARATION OF PERFORMANCE

DoP 00037

FIBRAPLAST

Manufactured at:



FINSA PADRÓN Paraíso s/n 15900 Padrón. A Coruña. Spain	FINSA OREMBER Pol. Ind. San Cibrao das Viñas 32911 Ourense. Spain	FINSA FIBRANOR Pol. Ind. de Rábade 27370 Rábade. Lugo. Spain	LUSO FINSA - NELAS Est. Nac. 234, km. 92.7 3524-952 Nelas. Portugal
---	--	---	--

Product type	Intended use	AVCP*
MDF	Internal use as non structural components in dry conditions	4

*Assessment and verification of constancy of performance system according to Annex V of regulation (EU) No 305/2011

Declared performance:

Essential characteristics	Performance								Harmonised technical specification EN 13986:2004
	Thickness (mm)								
	units	>2.5 to 4	>4 to 6	>6 to 9	>9 to 12	>12 to 19	>19 to 30	>30 to 45	
Bending strength - EN 310	N/mm ²	23	23	23	22	20	18	17	
Modulus of elasticity - EN 310	N/mm ²	-	2700	2700	2500	2200	2100	1900	
Internal bond - EN 319	N/mm ²	0,65	0,65	0,65	0,60	0,55	0,55	0,50	
Swelling in thickness 24 hours - EN 319	%	35	30	17	15	12	10	8	
Release of formaldehyde EN 14322 Emission EN 717-2	Class mg/(h.m ²)	E1 <3.5	E1 <3.5	E1 <3.5	E1 <3.5	E1 <3.5	E1 <3.5	E1 <3.5	
Reaction to fire -Commission Decision 2007/348/EC- EN 13501-1:2007	Class Class	E Efl	E Efl	E Efl	D-s2,d0* Dfl,s1	D-s2,d0** Dfl,s1	D-s2,d0 Dfl,s1	D-s2,d0 Dfl,s1	
Water vapour permeability Wet cup / Dry cup Table 9, EN 13986:2004	μ	21/31	20/30	18/28	17/27	16/25	15/24	15/24	
Airborne sound insulation (surface mass) (R) 5.10, EN 13986:2004	db	NPD	NPD	22/24	24/26	26/28	29/30	30/33	
Sound absorption Frequency range 250Hz to 500Hz Table 10, EN 13986:2004	α	0.1	0.1	0.1	0.1	0.1	0.1	0.1	
Sound absorption Frequency range 1000Hz to 2000Hz Table 10, EN 13986:2004	α	0.20	0.20	0.20	0.20	0.20	0.20	0.20	
Thermal conductivity (λ) Table 11, EN 13986:2004	W/(m.K)	0.15	0.15	0.13	0.13	0.12	0.12	0.12	
Biological durability	Use classes	1	1	1	1	1	1	1	
Content of pentachlorophenol (PCP)	ppm	<5	<5	<5	<5	<5	<5	<5	

(*): Mounted without an air gap behind the FIBRAPLAST. Mounted with a closed air gap not more than 22 mm behind the FIBRAPLAST classification D-s2,d2. Classification E for any other more restrictive condition

(**): Mounted without an air gap behind the FIBRAPLAST, or with a closed air gap behind the FIBRAPLAST for thicknesses equal or greater than 15mm or with an open air gap behind the FIBRAPLAST for thicknesses equal or greater than 18 mm. Mounted with a closed air gap not more than 22 mm behind the FIBRAPLAST classification D-s2,d2 in thicknesses between 10 and 18 mm.

The performance of the product FIBRAPLAST is in conformity with the above declared performance.
This declaration of performance is issued under the sole responsibility of Financiera Maderera, S.A. -FINSA-

Javier Portela
FINSA IDi + Quality Director
Santiago de Compostela, January 2nd 2014